

Product Description

CAPILENE® CT 80 A is a specialty polypropylene combining typical advantages of polypropylene random and heterophasic copolymers.

Features:	Excellent impactVery low stress whiteningMold releaseGood organoleptic properties	Excellent transparencyHigh glossClarifiedShort cycle time
Uses:	Thin wall packagingLarge storage boxesClear pailsFood packaging	Heavy duty toolboxesCaps and closuresToysContainers

Processing Methods: Injection molding

Properties			Method	Typical Value*	Unit
Physical					
Melt Flow Rate		(230°C/2.16 kg)	ISO 1133	25	g/10 min
Mechanical					
Tensile Stress at Yield		(50 mm/min)	ISO 527-2	24	MPa
Tensile Strain at Yield		(50 mm/min)	ISO 527-2	17	' %
Flexural Modulus		(5 mm/min)	ISO 178	900	МРа
Izod Impact Strength,	notched	(+23°C)	ISO 180	18	kJ/m²
Izod Impact Strength,	notched	(0°C)	ISO 180	ϵ	kJ/m²
Izod Impact Strength,	notched	(-20°C)	ISO 180	3	kJ/m²
Thermal					
Vicat Softening Tempe	rature	(10 N)	ISO 306	131	°C
Heat Deflection Tempe	rature	(0.45 MPa)	ISO 75-2	71	°C
Optical					
Haze		(1 mm plaque)	ASTM D1003	12	%

^{*}Typical values; not to be construed as specifications.

Health, Quality, Regulations and Safety

This product is not classified as dangerous substance. Material safety data sheets, international standards certificates (e.g. ISO 9001) and other regulatory documents are available on our website. This product is not intended for use in medical or pharmaceutical applications and we do not support its use for such applications.

Website: http://www.Carmel-Olefins.co.il

Email: techserv@caol.co.il

Date: June 2017 Carmel Olefins Ltd. POB 1468 Haifa 31014 Israel