

## DOWLEX™ 2107GC Linear Low Density Polyethylene Resin

### Overview

DOWLEX™ 2107GC is processable at high line speeds. Films made from DOWLEX 2107GC Polyethylene Resin exhibit excellent stretchability, outstanding tear and impact resistance, as well as exceptional optical properties.

#### Main Characteristics:

- Linear Low Density Polyethylene

#### Applications:

- Cast Stretch Wrap Film

#### Complies with:

- U.S. FDA FCN 424
- EU, No 10/2011
- Consult the regulations for complete details.

### Additive

- Antiblock: No
- Slip: No
- Processing Aid: No

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.917 g/cm <sup>3</sup>	0.917 g/cm <sup>3</sup>	ASTM D792
Base Density	0.917 g/cm <sup>3</sup>	0.917 g/cm <sup>3</sup>	Dow Method <sup>1</sup>
Melt Index (190°C/2.16 kg)	2.3 g/10 min	2.3 g/10 min	ASTM D1238
Films	Nominal Value (English)	Nominal Value (SI)	Test Method
Film Thickness - Tested	0.91 mil	23 µm	
Tensile Strength			ASTM D882 <sup>2</sup>
MD : Yield, 0.91 mil (23 µm)	914 psi	6.30 MPa	
TD : Yield, 0.91 mil (23 µm)	856 psi	5.90 MPa	
MD : Break, 0.91 mil (23 µm)	6240 psi	43.0 MPa	
TD : Break, 0.91 mil (23 µm)	4060 psi	28.0 MPa	
Tensile Elongation			ASTM D882 <sup>2</sup>
MD : Break, 0.91 mil (23 µm)	470 %	470 %	
TD : Break, 0.91 mil (23 µm)	900 %	900 %	
Dart Drop Impact (0.91 mil (23 µm))	200 g	200 g	ASTM D1709A <sup>4</sup>
Elmendorf Tear Strength			ASTM D1922 <sup>3</sup>
MD : 0.91 mil (23 µm)	410 g	410 g	
TD : 0.91 mil (23 µm)	540 g	540 g	
Film Stretch Performace - Max Elongation	240 %	240 %	Dow Method <sup>4</sup>
Film Stretch Performace - Max Stretch to Puncture	130 %	130 %	Dow Method <sup>5</sup>
Optical	Nominal Value (English)	Nominal Value (SI)	Test Method
Gloss (45°, 0.906 mil (23.0 µm))	92	92	ASTM D2457
Haze (0.906 mil (23.0 µm))	0.70 %	0.70 %	ASTM D1003
Extrusion	Nominal Value (English)	Nominal Value (SI)	
Melt Temperature	428 to 536 °F	220 to 280 °C	

### Extrusion Notes

#### Fabrication Conditions For Cast Film:

- Melt Temperature: 220-280°C
- Chill Roll Temperature: 20-60°C
- Line Speed 150-450 m/min
- Recommended Gauge Range: 10-60 µm

## Notes

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

---

<sup>1</sup> Base density is estimated using the assumption that every 1000 ppm of antiblock in the finished product raises the density of the polymer by 0.0006 g/cm<sup>3</sup>. Base density is the estimated density of the polymer if it did not contain any antiblock.

---

<sup>2</sup> Cast film, 250 m/min; Chill roll 25°C.

---

<sup>3</sup> Method B; Cast film, 250 m/min; Chill roll 25°C.

---

<sup>4</sup> Cast film, 250 m/min; Chill roll 25°C; Measured on test stand.

---

<sup>5</sup> Cast film, 250 m/min; Chill roll 25°C; Measured on test stand; Max pre-strech before sharp probe penetrates.

---

## Product Stewardship

The Dow Chemical Company and its subsidiaries ("Dow") has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our Product Stewardship program rests with each and every individual involved with Dow products — from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

## Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

## Medical Applications Policy

NOTICE REGARDING MEDICAL APPLICATION RESTRICTIONS: Dow will not knowingly sell or sample any product or service ("Product") into any commercial or developmental application that is intended for:

- long-term or permanent contact with internal bodily fluids or tissues. "Long-term" is contact which exceeds 72 continuous hours;
- use in cardiac prosthetic devices regardless of the length of time involved ("cardiac prosthetic devices" include, but are not limited to, pacemaker leads and devices, artificial hearts, heart valves, intra-aortic balloons and control systems, and ventricular bypass-assisted devices);
- use as a critical component in medical devices that support or sustain human life; or
- use specifically by pregnant women or in applications designed specifically to promote or interfere with human reproduction.

Dow requests that customers considering use of Dow products in medical applications notify Dow so that appropriate assessments may be conducted. Dow does not endorse or claim suitability of its products for specific medical applications. It is the responsibility of the medical device or pharmaceutical manufacturer to determine that the Dow product is safe, lawful, and technically suitable for the intended use. **DOW MAKES NO WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY OF ANY DOW PRODUCT FOR USE IN MEDICAL APPLICATIONS.**

## Disclaimer

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the Customer is responsible for determining whether products and the information in this document are appropriate for the Customer's use and for ensuring that the Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Dow assumes no obligation or liability for the information in this document. **NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**

NOTICE: If products are described as "experimental" or "developmental": (1) product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; (3) there is greater potential for Dow to change specifications and/or discontinue production; and (4) although Dow may from time to time provide samples of such products, Dow is not obligated to supply or otherwise commercialize such products for any use or application whatsoever.

## Additional Information

<b>North America</b>		<b>Europe/Middle East</b>	+800-3694-6367
U.S. & Canada:	1-800-441-4369		+31-11567-2626
	1-989-832-1426	Italy:	+800-783-825
Mexico:	+1-800-441-4369		
<b>Latin America</b>		<b>South Africa</b>	+800-99-5078
Argentina:	+54-11-4319-0100		
Brazil:	+55-11-5188-9000		
Colombia:	+57-1-219-6000	<b>Asia Pacific</b>	+800-7776-7776
Mexico:	+52-55-5201-4700		+603-7965-5392

[www.dowplastics.com](http://www.dowplastics.com)

This document is intended for use within Europe

Published: 2010-03-09

© 2014 The Dow Chemical Company

