

# ExxonMobil™ HDPE HMA 035

## High Density Polyethylene Resin

### Product Description

HMA 035 is a UV stabilized HDPE grade, characterized by excellent dimensional stability, very high stiffness and good impact strength.

### General

Availability	• Africa & Middle East	• Asia Pacific	• Europe
Additive	• Thermal Stabilizer: Yes	• UV Stabilizer: Yes	
Applications	• Industrial Pails	• Vegetable and Bottle Crates	
Revision Date	• March 2010		

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.964 g/cm <sup>3</sup>	0.964 g/cm <sup>3</sup>	ExxonMobil Method
Melt Index (190°C/2.16 kg)	8.0 g/10 min	8.0 g/10 min	ASTM D1238
Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Heat Deflection Temperature (0.45 MPa)	162 °F	72.0 °C	ISO 75-2/B
Melting Temperature	273 °F	134 °C	ASTM D3418
Molded Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Stress at Yield	3770 psi	26.0 MPa	ISO 527-2/1A/50
Tensile Strain at Yield	9.0 %	9.0 %	ISO 527-2/1A/50
Tensile Strain at Break	> 100 %	> 100 %	ISO 527-2/1A/50
Flexural Modulus	160000 psi	1100 MPa	ISO 178
Environmental Stress-Crack Resistance 10% Igepal	3.00 hr	3.00 hr	ASTM D1693
Impact	Typical Value (English)	Typical Value (SI)	Test Based On
Notched Izod Impact Strength	3.3 ft-lb/in <sup>2</sup>	7.0 kJ/m <sup>2</sup>	ISO 180/1A

### Additional Information

The molded properties were measured on 4 mm (157.5 mil) thick injection molded specimen based on ISO 294-1.

- 0.45 MPa, 70 psi
- ESCR was measured on 2 mm (78.7 mil) thick compression molded plate (F50, 10 % Igepal, 50°C, 122°F)

### Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

### Notes

<sup>1</sup> Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

Typical properties: these are not to be construed as specifications.

© 2010 Exxon Mobil Corporation. To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. You may not copy this document to a Web site. ExxonMobil does not guarantee the typical (or other) values. Analysis may be performed on representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no endorsement of any product or process, and we expressly disclaim any contrary implication. The terms, "we", "our", "ExxonMobil Chemical", or "ExxonMobil" are used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliates they directly or indirectly steward. ExxonMobil, the ExxonMobil Chemical Emblem, the "Interlocking X" Device, Enable, Exceed, Exact, Exxco, Escorene, Escor, lotek, NTX, Polybilt, Paxon and Optema are trademarks or service marks of Exxon Mobil Corporation.