

Pakro Kimya Dış Ticaret A.Ş.

Vİstoç Ticaret Merkezi Aktem Plaza Kat:5 Daire:33 Bağcılar/İstanbul

ExxonMobil[™] LLDPE LL 1004AY Cast Linear Low Density Polyethylene Resin

ExonMobil

Product Datasheet

Product Description

LL 1004AY is an LLDPE grade, offering excellent high temperature stability. Properties may be further enhanced by combining with Exceed™ mLLDPE. TnPP is not intentionally added to LL 1004AY resin.

General						
Availability ¹		 Africa & Middle East 		 Europe 	Latin America	
Additive		 Antiblock: No 		 Slip: No 	Thermal Stabilizer: Yes	
Applications		Cast FilmCast Stretch Film		Food PackagingForm Fill And Seal Packaging	General Packaging	
Revision Date	•	06/30/2016				
k.						
Resin Properties		Typical Value	(English)	Typical Value	(SI)	Test Based On
Density		0.918	g/cm³	0.918	g/cm³	ASTM D1505
Melt Index (190°C/2.16 kg)	1.00	2.8	g/10 min	2.8	g/10 min	ASTM D1238
Peak Melting Temperature		248	°F	120	°C	ExxonMobil Method
Film Properties		Typical Value	(English)	Typical Value	(SI)	Test Based On
Tensile Strength at Break MD		7400	psi	50	MPa	ASTM D882
Tensile Strength at Break TD		3300	psi	23	MPa	ASTM D882
Elongation at Break MD		530	%	530	%	ASTM D882
Elongation at Break TD		840	%	840	%	ASTM D882
Secant Modulus MD - 1% Secant		20000	psi	140	MPa	ASTM D882
Secant Modulus TD - 1% Secant		21000	psi	150	MPa	ASTM D882
Dart Drop Impact		40	g	40	g	ASTM D1709A
Elmendorf Tear Strength MD		40	g	40	g	ASTM D1922
Elmendorf Tear Strength TD		340	g	340	g 🔒	ASTM D1922
Optical Properties		Typical Value	(English)	Typical Value	(SI)	Test Based On
Gloss (45°)		95		95	1	ASTM D2457
Haze		1.7	%	1.7	%	ASTM D1003

Legal Statement

This product is not intended for use in medical applications and should not be used in any such applications.

Tris(nonylphenol)phosphite (TNPP) CAS# 26523-78-4 is not intentionally used by ExxonMobil in this product. Although this product is not routinely tested for its presence, based on product composition knowledge this substance is not expected to be present. However, the fact that this substance is not intentionally used by ExxonMobil in this product does not exclude that trace levels of this substance may be present as a result of the specific characteristics of the raw materials and/or of the manufacturing process.

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

Processing Statement

The film properties have been measured in a 21 µm (0.83 mil) thick cast film, extruded on a cast film line at 238 m/min (780 ft/min) line speed and temperature setting of 288 °C (550 F).

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

ExxonMobil™ LLDPE LL 1004AY Cast

Linear Low Density Polyethylene Resin

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2020 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical" and "ExxonMobil" are each used for convenience.

exxonmobilchemical.com

