

Pakro Kimya Dış Ticaret A.Ş.

İstoç Ticaret Merkezi Aktem Plaza Kat:5 Daire:33 Bağcılar/İstanbul

ExxonMobil[™] PP5032E3 Polypropylene Homopolymer



Product Description

PP 5032E3 is a polypropylene homopolymer type designed for production of monofilaments, tapes for the textile industry, geo textiles, fibrillated tapes for ropes and twines in the packaging, agriculture and fishing industries and suitable for chill roll and water bath lines.

| General | | | | | | |
|---|--|---|---------------|-------------------|----------------------|--|
| Availability ¹ | Africa & Middle East | • Asia F | acific | | | |
| Features | Low Water Carryover | | | | | |
| Uses | Consumer ApplicationFabrics | Consumer Applications• FibersFabrics• Heavy-duty Bags | | Packaging | | |
| Appearance | Natural Color | | | / | | |
| Form(s) | • Pellets | | | | | |
| Processing Method | • Extrusion | Extrusion • Filament Extrusion • Thermoforming | | | | |
| Revision Date | • 03/01/2010 | | | | | |
| Dhysical | Typical V-h- | (En aliah) | Typical Value | | Test Based On | |
| Physical Melt Mass-Flow Rate (MFR) (230°C/2.16 | Typical Value | g/10 min | V 1 | (SI) g/10 min | ISO 1133 | |
| Density | | g/cm ³ | | g/cm ³ | ExxonMobil Method | |
| | 4 | | | | | |
| Mechanical | Typical Value | (English) | Typical Value | (SI) | Test Based On | |
| Tensile Stress at Yield | 4790 | psi | 33.0 | MPa | ISO 527-2/1A/50 | |
| Tensile Strain at Yield | 9.0 | % | 9.0 | % | ISO 527-2/1A/50 | |
| Tensile Modulus | 209000 | psi | 1440 | MPa | ISO 527-2/1A/1 | |
| Flexural Modulus (0.079 in/min (2.0 mm/n | nin)) 207000 | psi | 1430 | MPa | ISO 178 | |
| | | | | | J | |
| Impact | Typical Value | | Typical Value | × / | Test Based On | |
| Charpy Notched Impact Strength (73°F (23°C)) | 2.1 | ft·lb/in ² | 4.5 | kJ/m ² | ISO 179/1eA | |
| | | | | | | |
| Thermal | Typical Value | (English) | Typical Value | (SI) | Test Based On | |
| Peak Melting Temperature | 320 | °F | 160 | °C | ASTM D3418 | |
| Heat Deflection Temperature (0.45 MPa) | 187 | °F | 86.0 | °C | ISO 75-2/B | |
| | | | | | | |
| Hardness | Typical Value | (English) | Typical Value | (SI) | Test Based On | |
| Shore Hardness (Shore D, 15 sec) | 70 | | 70 | | ISO 868 | |

Legal Statement

This product is not intended for use in medical applications and should not be used in any such applications.

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

ExxonMobil™ PP5032E3

E%onMobil

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2019 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com

