

ExxonMobil LDPE

LD 653 series

Injection Molding Resin

Description

LD 653 series are medium flow LDPE grade, characterized by high stiffness and good toughness.

Applications

tough medium sized moldings

ExonMobil

- caps
- bottle closures
- toys
- houseware

| Additive Package | Antiblock | Slip | Thermal Stabilizer |
|------------------|-----------|-----------|--------------------|
| LD 653 | No | No | No |
| LD 653CE | No | 525 ppm 🦯 | No |

| Resin Properties | Test Based On | Typical Value / Unit | |
|--------------------------|--------------------|--------------------------|--|
| Melt Index | ASTM D1238 | 22 g/10 min | |
| Density | ASTM D4703 / D1505 | 0.9235 g/cm ³ | |
| Peak Melting Temperature | ASTM D3418 | 109 °C 228 °F | |
| Crystallization Point | ASTM D3418 | 94 °C 201 °F | |
| Vicat Softening Point | ISO 306-A50 | 91 °C 196 °F | |
| | | _ | |

Molded Properties

| Tensile Strength | ISO 527-2/1A/50 | 9 MPa | 1300 psi |
|-----------------------------|-----------------|---------|-----------|
| Elongation @ Break | ISO 527-2/1A/50 | 120 % | |
| E-Modulus (0.05-0.25 %) | ISO 527-2/1A/1 | 200 MPa | 29000 psi |
| Shore Hardness - D (15 sec) | ISO 868 | | 44 |

The molded properties have been measured on 4 mm (157.5 mil) thick injection molded specimen, based on ISO 1872-2.

LD 653 series can - in principle - be used in food contact applications in various EU Member States and in the USA (FDA). Migration or use limitations may apply. Please contact your ExxonMobil Chemical representative for more detailed information and/or actual compliance certification documents for the specific grade of interest.