

Pakro Kimya Dış Ticaret A.Ş.

İstoç Ticaret Merkezi Aktem Plaza Kat:5 Daire:33 Bağcılar/İstanbul

# Eltex® PF1315AA

## **Product Technical Information**

 $C_6$  m-LLDPE for extrusion coating, injection moulding and compounding with a basic antioxidant additive package

# Applications

extrusion coating polymer for high demand on sealing and mechanical performance

# **Benefits and Features**

- outstanding ESCR performance
- improved sealing performance
- improved mechanical properties

We recommend that you consult your INEOS technical representative for further advice on the use of **Eltex® PF1315AA**.

Properties		Test Method	Value	Units
<b>Physical</b> Melt Flow Rate Density	(190°C/2,16kg)	ISO 1133 ISO 1183	15 914	g/10min kg/m³
		Conditioning ISO 1872/1		
Mechanical				
Shore Hardness D		ISO 868	46	
Tensile Modulus		ISO 527	217	MPa
Tensile Stress	@ yield	ISO 527	9	MPa
Elongation	@ yield		22	%
Tensile Stress	@ break	ISO 527	no break	MPa
Elongation	@ break	ISO 527	>600	%
Flexural Modulus	(23°C)	ISO 178	245	MPa
Izod Impact Strength	(-20°C)	ISO 180	71	kj/m <sup>2</sup>
ESCR (Environmental Stree	ss Crack Resistance)	INEOS Test Method	175	h
Thermal				
DSC Melting Point		INEOS Test Method	96 114	°C
Heat of Fusion		ASTM 3418	104	J/g
Crystallisation Point		INEOS Test Method	100 84	°C
Vicat Softening Point		ISO 306 Method A	90	°C

Data should not be used for specification work.

☐ Measurements made on compression moulded plaques

October 2009

Published by

# Eltex® PF1315AA

### **Extrusion conditions**

For extrusion coating it is recommended to avoid extrusion temperatures above 300°C, not to jeopardize the sealing properties.

For injection moulding it is recommended to avoid extrusion temperatures above 280°C.

### Storage

**Eltex® PF1315AA** should be stored in a dry and dust free environment at temperatures below 50°C. Exposure to direct sunlight should be avoided, as this may lead to product deterioration.

#### **Regulatory Information**

The product and uses described herein may require global product registrations and notifications for chemical inventory listings, or for use in food contact or medical devices. For further information, send an email to <u>psnohreg@ineos.com</u>. Unless specifically indicated, the products mentioned herein are not suitable for applications in the medical or pharmaceutical sector.

#### Health and Safety Information

The product described herein may require precautions in handling. The available product health and safety information for this material is contained in the Material Safety Data Sheet (MSDS) that may be obtained from the website <u>www.ineospolyolefins.com</u>. Before using any material, a customer is advised to consult the MSDS for the product under consideration for use.

#### **Exclusion of Liability**

Although INEOS O&P Europe endeavours to ensure that all information and advice relating to our materials or other materials howsoever provided to you by INEOS O&P Europe is accurate and up to date, no representation or warranty, express or implied is made by INEOS O&P Europe as to its accuracy or completeness. All such information and advice is provided in good faith and INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action you may take as a result of relying on such information or advice or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

In addition data and numerical results howsoever provided to you by INEOS O&P Europe are given in good faith and are general in nature. Data and numerical results are not and shall not be regarded as specifications and as such INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action that you take as a result of relying on such data and results or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

It remains at all times your responsibility to ensure that INEOS O&P Europe materials are suitable for the particular purpose intended and INEOS O&P Europe shall not be responsible for any loss or damage caused by misuse of INEOS O&P Europe products. To the maximum extent permitted by law, INEOS O&P Europe accepts no liability whatsoever arising out of the application, adaptation or processing of the products described herein, the use of other materials in lieu of INEOS O&P Europe materials or the use of INEOS O&P Europe materials in conjunction with such other materials.

October 2009

Published by

