

Eltex[®] PF6130AA

Product Technical Information

Applications

Eltex[®] PF6130AA is particularly suitable for high performance cast stretch film applications and both extruded structures.

It also can be used for the production of artificial grass monofilaments.

Benefits and Features

Eltex[®] PF6130AA is a polyethylene copolymer containing hexene-1 as the comonomer a metalocene with catalyst.

Eltex[®] PF6130AA offers the following

- properties:
- High stretchability in cast film applications
- High holding force
- Good web stability during extrusion
- Excellent overall film appearance and surface finish
- High output rates
- Very high puncture resistance

We recommend that you consult your INEOS technical representative for further advice on the use of Eltex[®] PF6130AA.


Properties	Test Method	Value	Units
Physical			
Melt flow rate			
Condition 4	ISO 1133	3.5	g/10 min
Conventional Density	ISO 1872-1	918	kg/m ³
Additives:			
antioxidants			
Film*			
Dart drop impact	Method A	ASTM D1709	600
Puncture resistance		INEOS method	28
Tensile stress @ break		ISO 1184	40/20
MD/TD			
MD/TD		ISO 1184	300/400
1% Secant modulus	MD/TD	ISO 1184	115/120
Elmendorf tear strength	MD/TD	ASTM D1922	260/430
Haze		ASTM D1003	1
Gloss (45°)		ASTM D2457	93

- Data should not be used for specification work

* 20 µm film, 230°C melt temperature - MD = machine direction, TD = transverse

direction
April 2013

Published by



Eltex[®] PF6130AA

Extrusion conditions

Eltex[®] PF6130AA should be processed on machinery purpose designed for LLDPE. The product is melt stabilized, melt temperatures in the range 230 - 280°C can be used.

Storage

The product should be stored in a dry and dust free environment at temperature below 50°C. Exposure to direct sunlight should be avoided as this may lead to product deterioration. It is advised to process the product within maximum one year after delivery.

Regulatory Information

The product and uses described herein may require global product registrations and notifications for chemical inventory listings, or for use in food contact or medical devices. For further information, send an email to psnohreg@ineos.com.

Unless specifically indicated, the products mentioned herein are not suitable for applications in the medical

Health and Safety Information

The product described herein may require precautions in handling. The available product health and safety information for this material is contained in the Material Safety Data Sheet (MSDS) that may be obtained from the website www.ineospolyolefins.com. Before using any material, a customer is advised to consult the MSDS for the product under

Consideration of Liability

Although INEOS O&P Europe endeavours to ensure that all information and advice relating to our materials or other materials howsoever provided to you by INEOS O&P Europe is accurate and up to date, no representation or warranty, express or implied is made by INEOS O&P Europe as to its accuracy or completeness. All such information and advice is

provided in good faith and INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any inaccuracy or data and numerical results howsoever provided to you by INEOS O&P Europe are given in good faith and are a result of relying on such information or advice or for any loss or damage, including any consequential loss. Data and numerical results are not and shall not be regarded as specifications and as such INEOS O&P Europe is not liable to you as a result of taking such action.

INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action that you take as a result of relying on such

data and results in any way, including any loss or damage, including any consequential loss, suffered by you or your party as a result of the

particular such purpose intended and INEOS O&P Europe shall not be responsible for any loss or damage caused by misuse of INEOS

O&P Europe products. To the maximum extent permitted by law, INEOS O&P Europe accepts no liability whatsoever

arising out of the application, adaptation or processing of the products described herein, the use of other materials in lieu

of INEOS O&P Europe materials or the use of INEOS O&P Europe materials in conjunction with such other materials.