

ExxonMobil™ LDPE LD 150 Series

Low Density Polyethylene Resin



Product Description

LD 150 series are LDPE grades, offering good blend mechanical properties and stiffness. Several additive packages are available according to the required surface properties.

General

Availability ¹	• Africa & Middle East	• Asia Pacific	• Europe
Additive	• LD 150BW: Antiblock: No; Slip: No; Thermal Stabilizer: Yes • LD 150AC: Antiblock: 450 ppm; Slip: 500 ppm; Thermal Stabilizer: Yes		
Applications	• Agricultural Film	• Collation Shrink	• Lamination Film
	• Blend Partner	• Form Fill And Seal Packaging	• Medium Duty Shrink Film
	• Co-Extrusion Films	• Freezer Film	• Shoppers
Form(s)	• Pellets		
Revision Date	• March 2010		

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.923 g/cm ³	0.923 g/cm ³	ExxonMobil Method
Melt Index (190°C/2.16 kg)	0.75 g/10 min	0.75 g/10 min	ASTM D1238
Peak Melting Temperature	228 °F	109 °C	ExxonMobil Method

Film Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Break MD	3480 psi	24.0 MPa	ASTM D882
Tensile Strength at Break TD	3340 psi	23.0 MPa	ASTM D882
Elongation at Break MD	370 %	370 %	ASTM D882
Elongation at Break TD	570 %	570 %	ASTM D882
Secant Modulus MD - 1% Secant	31900 psi	220 MPa	ASTM D882
Secant Modulus TD - 1% Secant	37700 psi	260 MPa	ASTM D882
Dart Drop Impact	180 g	180 g	ASTM D1709A
Elmendorf Tear Strength MD	200 g	200 g	ASTM D1922
Elmendorf Tear Strength TD	200 g	200 g	ASTM D1922

Optical Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Gloss (45°)	64	64	ASTM D2457
Haze	7.0 %	7.0 %	ASTM D1003

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Processing Statement

The test specimen were prepared on LD 150BW, 50µm (1.97mil) thick film, using a 200 mm (7.9 in) die, die gap of 1.0 mm (39.4 mil), Blow-Up Ratio of 2.5 and temperature profile of 145 - 180°C (293 - 356°F).

Typical properties: these are not to be construed as specifications.

© 2010 Exxon Mobil Corporation. To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. You may not copy this document to a Web site. ExxonMobil does not guarantee the typical (or other) values. Analysis may be performed on representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no endorsement of any product or process, and we expressly disclaim any contrary implication. The terms, "we", "our", "ExxonMobil Chemical", or "ExxonMobil" are used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliates they directly or indirectly steward. ExxonMobil, the ExxonMobil Chemical Emblem, the "Interlocking X" Device, Enable, Exceed, Exact, Exxco, Escorene, Escor, lotek, NTX, Polybilt, Paxon and Optema are trademarks or service marks of Exxon Mobil Corporation.

ExxonMobil Chemical ExxonMobil™ LDPE LD 150 Series Low Density Polyethylene Resin

Notes

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

For additional technical, sales and order assistance:

Worldwide and the Americas
ExxonMobil Chemical Company
13501 Katy Freeway
Houston, TX 77079-1398
USA
1-281-870-6050

Asia Pacific
ExxonMobil Chemical Singapore Pte. Ltd.
1 HarbourFront Place
#06-00 HarbourFront Tower One
Singapore 098633
86 21 240-75380

Europe, Middle East and Africa
ExxonMobil Chemical Europe
Hermeslaan 2
1831 Machelen, Belgium
420-239-016-274

Typical properties: these are not to be construed as specifications.

© 2010 Exxon Mobil Corporation. To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. You may not copy this document to a Web site. ExxonMobil does not guarantee the typical (or other) values. Analysis may be performed on representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no endorsement of any product or process, and we expressly disclaim any contrary implication. The terms, "we", "our", "ExxonMobil Chemical", or "ExxonMobil" are used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliates they directly or indirectly steward. ExxonMobil, the ExxonMobil Chemical Emblem, the "Interlocking X" Device, Enable, Exceed, Exact, Exxco, Escorene, Escor, Iotek, NTX, Polybilt, Paxon and Optema are trademarks or service marks of Exxon Mobil Corporation.