

Homopolymer

TELDENE

LyondellBasell Licensed Spheripol Process

H03TF

TDS



Typical Applications

- Extrusion and thermoforming applications
- Used for the production of fruit baskets, trays, transparent drinking cups and containers

Key Characteristics

- Nucleated Homopolymer
- Excellent Transparency and Processability
- Excellent Stiffness and dimensional stability
- Excellent isotropic shrinkage control
- Excellent for deep thermoforming application
- Food contact approval for specific applications (refer to NATPET)

Processing Methods

- Sheet Extrusion
- Thermoforming

Qualitative

Resin	Conditions	Method	Value	Unit
Density	23°C	ISO 1183	0.900	g/cm ³
Melt Flow Rate (MFR)	230°C/2.16 kg	ASTM 1238-10	3.1	g/10-min
Mechanical				
Flexural Modulus		ISO 178	1,720	MPa
Tensile Stress at Break	50-mm/min	ISO 527	27	MPa
Tensile Stress at Yield	50-mm/min	ISO 527	37	MPa
Tensile Strain at Break	50-mm/min	ISO 527	> 50	%
Tensile Strain at Yield	50-mm/min	ISO 527	9	%
Izod <i>Notched</i>	23°C	ASTM D 256	5.1	kJ/m ²
Thermal				
Heat Deflection Temperature	0.45 MPa Un-annealed	ISO 75B	90	°C
Vicat Softening Temperature	A50 (50°C/h 10N)	ISO 306	154	°C
Additional				
Tensile Modulus	1-mm/min	ISO 527	1,600	MPa

Note

The above are typical data representing the product; not to be construed as analysis certificate or specifications.

For further details about NATPET and its products, please visit the website at www.natpetpp.com

Homopolymer

TELDENE

LyondellBasell Licensed Spheripol Process

H03TF

TDS



Special Features

- Thermoforming
 - Tested on Amut S.p.A machine AMP630 and performed well
- Shows broad processing window while providing excellent mechanical properties and transparency

Processing Conditions

Average injection temperature range may be kept between 230 - 240°C.

Food Regulation

This product is defined as a preparation under specific food contact regulation. Detailed information will be provided in a relevant document "Regulatory Compliances Product Declaration" on request.

Storage and Handling

Polypropylene resin should be stored to prevent a direct exposure to sunlight and heat. Please refer to "Material Safety Datasheet" (MSDS) for handling and storage information.

Documents

Legal documents, MSDS, trial reports and machine builder certificate are available on request. Please send your request to the following e-mail: technicalsupport@natpetpp.com

For further details about NATPET and its products, please visit the website at www.natpetpp.com

NATPET® products, marketed under the trade name Teldene®, are intended for the use by those customers and/or any other consumers, who undertake to become responsible to independently establish on their own the appropriateness of the product for its intended use, covering all safety and legally enacted requirements at the location of its projected use and the legal disposal practices thereof. The description of the product as given in this sheet shall under no circumstances be construed as warranty, express or implied including a warranty of merchandize fitness for a particular purpose. On behalf of NATPET, no one is authorized to make any such warranties, or take up on their own to assume such a liability. In case of product related claims, the sole and maximum remedy will be the physical substitution of the product or reimbursement of the purchase value, as per NATPET's options. Further claims based on consequential, secondary, castigatory, or extraordinary damages will in no way entertained by NATPET. NATPET would like to advise its customers and other users that unless specifically stated the supplied products should not be used for applications in medical and/or pharmaceutical sectors.