

Technical Data Sheet

Moplen HP515M

Polypropylene, Homopolymer



Product Description

Moplen HP515M is a polypropylene homopolymer containing slip and anti-blocking additives.

Moplen HP515M is typically used by customers for cast films. Moplen HP515M is used by customers in many different applications, such as packaging and lamination films for foodstuffs (pasta, snacks, biscuits, bakery products and confectionery), or film for packaging of flowers and books stationery.

Films made with Moplen HP515M have been reported by customers to exhibit very high transparency and high gloss.

Regulatory Status

For regulatory compliance information, see Moplen HP515M [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Africa-Middle East; Europe
Application	Food Packaging Film; Lamination Film; Stationery Film; Textile Packaging Film
Market	Flexible Packaging
Processing Method	Cast Film
Attribute	Controlled Rheology; Good Stiffness; High Clarity; High Gloss; Homopolymer; Unspecified Antiblocking; Unspecified Slip

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	9.0	g/10 min	ISO 1133-1
Density	0.90	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus	1300	MPa	ISO 178
Tensile Stress at Break	19	MPa	ISO 527-1, -2
Tensile Stress at Yield	32	MPa	ISO 527-1, -2
Tensile Strain at Break	600	%	ISO 527-1, -2
Tensile Strain at Yield	11	%	ISO 527-1, -2
Thermal			
Vicat Softening Temperature, (A/50 N)	153	°C	ISO 306
Heat Deflection Temperature B, (0.45 MPa, Unannealed)	85	°C	ISO 75B-1, -2

Notes

These are typical property values not to be construed as specification limits.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.