

Technical Data Sheet

Moplen HP561R

Polypropylene, Homopolymer



Product Description

Moplen HP561R is a polypropylene homopolymer used for extrusion applications. Moplen HP561R has a very narrow molecular weight distribution and is formulated with an anti-gasfading stabilisation package. Moplen HP561R is used for the production of continuous filaments. Typical applications are high-tenacity yarns (HTY) and spunbond nonwovens.

Regulatory Status

For regulatory compliance information, see Moplen HP561R [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

This grade is not intended for medical and pharmaceutical applications.

| | |
|-------------------|---|
| Status | Commercial: Active |
| Availability | Africa-Middle East; Asia-Pacific; Europe |
| Application | Absorption & Filtration; Filament Yarn; Furniture & Buildings; Geotextile & Agriculture; Hygiene Nonwoven; Nonwovens; Wipes/Tissues |
| Market | Textile |
| Processing Method | Continuous Filament/Spinning; Extrusion Coating; Fibers; Spunbond |
| Attribute | Controlled Rheology; Gas-fading Resistant; High Flow; Homopolymer; Narrow Molecular Weight Distribution |

| Typical Properties | Nominal Value | Units | Test Method |
|---|---------------|-------------------|---------------|
| Physical | | | |
| Melt Flow Rate, (230 °C/2.16 kg) | 25 | g/10 min | ISO 1133-1 |
| Density | 0.900 | g/cm ³ | ISO 1183-1 |
| Mechanical | | | |
| Flexural Modulus | 1200 | N/mm ² | ISO 178 |
| Tensile Stress at Break, (23 °C, 50 mm/min) | 20 | N/mm ² | ISO 527-1, -2 |
| Tensile Stress at Yield, (23 °C, 50 mm/min) | 33 | N/mm ² | ISO 527-1, -2 |
| Tensile Strain at Break, (23 °C, 50 mm/min) | 650 | % | ISO 527-1, -2 |
| Tensile Strain at Yield, (23 °C, 50 mm/min) | 11 | % | ISO 527-1, -2 |
| Thermal | | | |
| Vicat Softening Temperature, (A50) | 151 | °C | ISO 306 |
| Deflection Temperature Under Load, (0.45 MPa, Unannealed) | 74 | °C | ISO 75B-1, -2 |

Notes

These are typical property values not to be construed as specification limits.

Conveying:

Conveying equipment should be designed to prevent production and accumulation of fines and dust particles that are contained in polymer resins. These particles can under certain conditions pose an explosion hazard. Conveying systems should be grounded, equipped with adequate filters and regularly inspected for leaks.

Storage:

The resin is packed in 25 kg bags, octabins or bulk containers protecting it from contamination. If it is stored under certain conditions, i. e. if there are large fluctuations in ambient temperature and the atmospheric humidity is high, moisture may condense inside the packaging. Under these circumstances, it is recommended to dry the resin before use. Unfavorable storage conditions may also intensify the resin's slight characteristic odor.

Resin should be protected from direct sunlight, temperatures above 40°C and high atmospheric humidity during storage. Higher storage temperatures may reduce the storage time.

The information submitted is based on our current knowledge and experience. In view of the many factors that may affect processing and application, these data do not relieve processors of the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose. This information does not remove the obligation of the customer to inspect the material on arrival and notify us of any faults immediately. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.