



Pakro Kimya Dış Ticaret A.Ş.

İstoç Ticaret Merkezi Aktem Plaza Kat:5 Daire:33 Bağcılar/İstanbul

Formolene[®] 3335E

Random Copolymer for Clear Storage Containers and Food and Beverage Containers

Formolene® 3335E is a high melt flow random copolymer with fast cycle time and easy mold release. It is designed for injection molding including thin wall applications. The use of an advanced clarifier produces a material with low yellowness index and haze – which makes it an excellent choice for 'see-through' house wares and rigid packaging.

Formolene[®] 3335E meets the requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles and components of articles intended for direct food contact. For additional information on approved conditions of use for food contact applications, please refer to the "Products" section on our website (http://www.fpcusa.com/ourproducts.html).

This material is free of animal-derived content.

		Typical Values			
Property	Test Method	English		SI	
Melt Flow Rate, I ₂ @ 230°C	ASTM D1238	35	g/10 min	35	g/10 min
Density	ASTM D1505	0.9	g/cm ³	0.9	g/cm ³
Tensile Strength at Yield (50 mm/min)	ASTM D638	4,200	psi	29	MPa
Elongation at Yield (50 mm/min)	ASTM D638	15	%	15	%
Flexural Modulus (1.3 mm/min), 1% Secant	ASTM D790	150,000	psi	1035	MPa
Notched Izod Impact Strength @ 73°F	ASTM D256A	1.2	ft-lb/in	64	J/m
Heat Deflection Temperature @ 66 psi	ASTM D648	185	°F	85	°C
Plaque Haze, %	FPC method	12	%	12	%

Typical Properties of this Commercial Grade

Note: Specimens were injection molded according to the conditions specified in ASTM D4101. Data for representative purposes only; not to be construed as product specification. Published 7/12, Revised 3/18

Any inquiries regarding this data sheet should be addressed to: 9 Peach Tree Hill Road • Livingston, NJ 07039 • Phone: (888) FPCUSA3 • Fax: (973) 422-7772

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of FORMOSA PLASTICS CORPORATION, U.S.A. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting the results, FORMOSA PLASTICS CORPORATION, U.S.A. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties. The responsibility of FORMOSA PLASTICS CORPORATION, U.S.A. And the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties. The responsibility of FORMOSA PLASTICS CORPORATION, U.S.A. for claims arising out of breach of warranty, negligence, strict liability or otherwise is limited to the purchase price of the material. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.

© Formosa Plastics Corporation, U.S.A.