



Technical Data Sheet

Riblene® MP30
Low Density Polyethylene

DESCRIPTION

Riblene® MP30 is a medium fluidity low density polyethylene resin (LDPE).

APPLICATIONS

Riblene® MP30 is suitable for injection moulding and compound applications. Parts made by Riblene® MP30 are characterised by a medium rigidity. Riblene® MP30 is recommended for houseware, high gloss toys and medium thickness articles.

PROPERTIES

TYPICAL

Properties	Test Method	Typical value
Resin Properties		
Melt Flow Index _{190 °C / 2.16 kg} (g/10')	ASTM D1238	7.5
Density (g/cm ³)	ASTM D1505	0.925
Melting point (°C)	PE	112
Brittleness point (°C)	ASTM D746	<-65
Vicat softening point _{1kg} (°C)	ASTM D1525	92
Mechanical properties¹		
Tensile strength at yield (MPa)	ASTM D638	14.5
Flexural modulus (MPa)	ASTM D790	200
Hardness (Shore D)	ASTM D2240	50

¹ Values are referred to an injection moulded plaque
Actual properties are typical and may vary depending upon operating conditions and additive package.

PROCESSING CONDITIONS

Processing conditions are depending on several parameters: the shape of the part to be manufactured, the localisation of the injection point, the injection moulding machine and the cooling of the mould

Typical processing conditions:

Temperature profile of the barrel (°C) 160 - 220
Temperature of the mould (°C) 10 - 30

STORAGE AND HANDLING

Riblene® MP30 is supplied in pellet form. This material may readily be conveyed and bulk-fed through equipment designed for conventional pelletised polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping be practised throughout your facility.

Before using this product, read and understand the current POLIMERI EUROPA Safety Data Sheet for this product.

AVAILABILITY

Contact the POLIMERI EUROPA sales office nearest to you regarding availability and your specific application requirements.

FOOD CONTACT STATUS

Riblene® MP30 complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications. Certificates of compliance are available upon request.

TECHNICAL SERVICE

POLIMERI EUROPA SpA
Piazza Boldrini 1
20097 S. Donato Milanese (Milan)-Italy
Tel. +39 02 520.1
Fax +39 02 520.42436

POLIMERI EUROPA SAS
Route des Dunes BP59
F-59279 MARDYCK
France
Tel. +33 3 2823.5514
Fax +33 3 2823.5520

HEADQUARTERS

POLIMERI EUROPA SpA
Piazza Boldrini 1
20097 San Donato Milanese (Milan)-Italy
Tel. +39 02 520.1
Fax +39 02 520.42901
info.polyethylene@polimerieuropa.com
www.polimerieuropa.com

IMPORTANT: The descriptions and figures contained herein are provided to customer by way of a general information for the purposes the product is intended for. These reflect POLIMERI EUROPA's knowledge at the time of publication. Since the acknowledged various product applications by customers cannot be controlled by POLIMERI EUROPA, in no circumstances may POLIMERI EUROPA be held responsible for the results obtained from the customers manufacturing processes or for the product used in combination with other substances. By the information contained herein POLIMERI EUROPA won't release any warranty and/or any legal responsibility and/or give any suggestion on the use of the product, or grant any franchise on existing patents. The end-user, transformer shall always check the specific suitability of the product for the purposes it is intended for and its compatibility with process specifications. Moreover, the buyer shall check that retention, use or marketing of our products be in compliance with health, environmental as well as work-and-consumer-related safety requirements. It is the buyer's responsibility to inform end-user. In no circumstances will POLIMERI EUROPA be held responsible should not the buyer meet the obligations and recommendations indicated herein