







HD50MA180

HIGH DENSITY POLYETHYLENE

FOR HIGH FLOW INJECTION MOULDED PRODUCTS

HD50MA180 is a high flow High Density Polyethylene (HDPE) grade . This grade is specially formulated to manufacture large, intricate, thin walled multi cavity injection moulded products. It has narrow molecular weight distribution, which makes it easier to process and productsmanufactured have good gloss and rigidity.

Typical Characteristics*			
Property	Test Method	Unit	Typical Value **
Melt Flow Index (190°C/2.16 kg)	ASTM D1238	gm/10 min.	20.0
Density (23°C)	ASTM D1505	gm/cm ³	0.950
Tensile Strength at Yield	ASTM D638	MPa	22
Elongation at Break	ASTM D638	%	12
Flexural Modulus	ASTM D790	MPa	900
Notched Izod Impact Strength	ASTM D256	J/m	30
Vicat Softening Point	ASTM D1525	°C	123

^{*}Typical Characteristics and not to be taken as specifications

Applications

Houseware, storage bins, thin wall moulding.

RegulatoryInformation

• Meets the requirementsstipulated in standard IS:10146-1982 on "Specification for Polyethylene for safe use in contact with foodstuffs, pharmaceuticals, and drinking water". It also conforms to the positive list of constituents as prescribed in IS: 10141-1982. The grade and the additives incorporated in it also comply with the FDA:CFRTitle 21,177.1520, Olefin polymers.

Storage Recommendations

• Bags should be stored in dry/closed conditions at temperatures below 50°C and protected from UV/direct sunlight.

Reliance Industries Limited, Product - Application & Technology Group, PRTC, Swastik Mill Compound, V. N. Purav Marg, Chembur, Mumbai-400 071. Tel.: + 91-22-6767 7000. E-mail: polymer_patsupport@ril.com Website: www.ril.com

^{**}Mechanical Properties are on Injection Moulded Specimen

[•] The information and data presented herein is true and accurate to the best of our knowledge. No warranty or guarantee expressed or implied, is made regarding performance or other wise. This information and data maynot be considered as a suggestion to use our products without taking into account existing patents, or legalprovisions or regulations, whether nationalor international. • The user of any information and/or data is advised to obtain the latest details from any of the offices of the companyor its authorised agents, as the information and/or data is subject to change based on the research and development workundertaken by the company.