

Pakro Kimya Dış Ticaret A.Ş.

İstoc Ticaret Merkezi Aktem Plaza Kat:5 Daire:33 Bağcılar/İstanbul

0212 659 26 03

→ 0212 659 26 01-02 🌐 www.pakrokimya.com.tr 🖾 Info@pakrokimya.com.tr



Chemicals

ISPLEN[®] PP 070 G2M

ISPLEN[®] PP 070 G2M is a polypropylene homopolymer with a medium fluidity intended for injection moulding. It is characterised by good flow properties that enables to fill the mould easier. Articles manufactured with this grade have excellent chemical resistance, are easily decorated and can accept different colouring systems.

TYPICAL APPLICATIONS

ISPLEN[®] PP 070 G2M is widely used for the production of consumer goods such us:

- Food containers and rigid packaging.
- Toys and small appliances.
- Caps and closures.

Recommended melt temperature range from 210 to 250°C. Processing conditions should be optimised for each production line.

PROPERTIES	VALUE	UNIT	TEST METHOD
Concret			
General Melt Flow Rate (230 °C; 2.16 kg)	12	g/10 min	ISO 1133
Density	905	kg/m ³	ISO 1183
			1
Mechanical			
Flexural Modulus	1550	MPa	ISO 178
Charpy Impact Strength Notched 23 °C	2.5	kJ/m ²	ISO 179
Thermal			
Heat Deflection Temperature 0.45MPa	85	°C	ISO 75
Others			
Shore Hardness	68	D Scale	ISO 868

ISPLEN® PP 070 G2M complies with the European Directives regarding materials intended for contact with foodstuffs. For further information, please contact our Technical Service and Development Laboratory or our Customer Care Service.

STORAGE

ISPLEN[®] PP 070 G2M should be stored in a dry atmosphere, on a paved, drained and not flooded area, at temperatures under 60°C and protected from UV radiation. Storage under inappropriate conditions could initiate degradation processes which may have a negative influence on the processability and the properties of the transformed product.

November 2009

This information is offered in good faith and meant only as a guide. The transformer or user will be, in each case, responsible for the processing conditions and the final use of the product. Freedom under patents, copyright and registered designs cannot be assumed. Technical Service and Development: Repsol Technology Centre Ctra. de Extremadura A5, Km 18 28931 Móstoles, Madrid Tel. +34 91 348 86 00 Fax: +34 91 530 45 17 atdpo@repsol.com

Headquarters: Pº de la Castellana, 280 28046 Madrid Spain Tel. +34 91 348 29 56 www.chemicals.repsol.com Customer Care: sacrq@repsol.com