



# PP 519A (Provisional Data Sheet)

PP Homopolymer for Spunbond applications

## Product Description

PP 519A is a controlled rheology grade with narrow molecular weight distribution intended for spun bond fiber extrusion applications.

PP 519A has following features:

- Consistent processability
- Good thread line stability
- Good color consistency
- Good gas fading resistance

## Typical Applications

PP 519A can be found suitable for high speed production of fine filament spun bond fabrics having excellent tensile properties and softness.

## Typical data

Properties	Unit	Value <sup>(1)</sup>	ASTM Method
<b>Resin Properties</b>			
Melt Flow Rate @ 230°C & 2.16 kg load	g/10 min.	35	D 1238
Density @ 23°C	kg/m <sup>3</sup>	905	D 792
Tensile Strength @ Yield	MPa	31	D 638
Tensile Elongation @ Yield	%	10	D 638
Flexural Modulus (1% Secant)	MPa	1500	D 790A
Notched Izod Impact Strength @ 23°C	J/m	20	D 256
Rockwell Hardness, R-Scale	-	102	D 785
Vicat Softening Point	°C	154	D 1525B
Heat Deflection Temperature @ 455 KPa	°C	92	D 648

(1) Typical values; not to be construed as specification limits.

(2) Based on injection molded specimens.

## Processing Conditions

Average extrusion temperature range may be kept at 210 - 250°C. PP 519A is recommended for

Reicofil 4 spun bond machine at high line speeds for the production of low gsm SS spun bond fabrics.

## Food Regulation

PP 519A is suitable for Food contact application. Detailed information is provided in relevant Material Safety Datasheet and for additional specific information please contact SABIC local representative for certificate.

## **Storage and Handling**

PP resin should be stored to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably don't exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PP resin within 6 months after delivery.

---

Saudi Basic Industries Corporation, P.O.Box 5101, Riyadh 11422, Kingdom of Saudi Arabia  
Tel: 966 1 2258000  
Fax: 966 1 2259000

Technical Marketing  
Tel: 966 1 2659166  
Fax: 966 1 2653544  
Toll-free 800 1245577

PP Sales:  
Fax: 966 1 2258771  
Website: [www.sabic.com](http://www.sabic.com)

---

*NOTICE: The information and data contained herein are believed to be correct and given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of product, no warranty is given or is to be implied with respect to such information, nor do we offer any immunity against infringement.*

