



SABIC® PP PHC26

PP block copolymer for Injection moulding

Description: This grade combines very high impact resistance, also at low temperatures, with high stiffness and offers good flow properties. Due to its narrow molecular weight distribution, the very low tendency to warp and the excellent surface quality, SABIC® PP PHC26 is typically used in injection moulding of suitcase shells, crates & boxes and automotive parts.

Health, Safety and Food Contact regulations:

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site <http://www.SABIC-europe.com>

The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/ medical applications.

IMDS 80775790

Typical values

Revision 20140109

Properties	Unit (Si)	Values	Test methods
Polymer properties			
Melt flow rate (MFR) at 230 °C and 2.16 kg	g/10 min	8.0	ASTM D 1238
Density	kg/m ³	905	ASTM D 792
Formulation			
UV stabilized	-	No	-
Anti static agent	-	No	-
Nucleating agent	-	Yes	-
Mechanical properties			
Tensile test			ASTM D 638
stress at yield	MPa	22	
strain at yield	%	6	
secant modulus at 1% elongation	MPa	1300	
Izod impact notched			ASTM D 256A
at 23 °C	J/m	No Break	
at 0 °C	J/m	200	
at -20 °C	J/m	110	
Rockwell hardness			ASTM D 785
R-scale	-	85	
Thermal properties			
Heat deflection temperature			ASTM D 648
at 1.80 MPa (HDT/A)	°C	55	
at 0.45 MPa (HDT/B)	°C	90	
Vicat softening temperature			ASTM D 1525
at 10 N (VST/A)	°C	147	
at 50 N (VST/B)	°C	68	

- 1) Speed of testing: 50 mm/min
2) Speed of testing: 5 mm/min
3) Temperature rate: 120°C/h



SABIC® PP PHC26

PP block copolymer for Injection moulding

Quality:

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

Storage and handling:

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

Disclaimer. The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC as referred to herein means any legal entity belonging to the group of companies headed by SABIC Europe B.V.