









## **SABIC® PP PHC27**

PP block copolymer for Injection moulding

## **Description:**

This grade combines very high impact resistance, also at low temperatures, with a good stiffness and offers very good flow properties. Due to its narrow molecular weight distribution and very low tendency to warp, it is highly suitable for injection moulding of crates, boxes, suitcase shells and automotive parts.

## Health, Safety and Food Contact regulations:

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site http://www.SABIC-europe.com

**Typical values** Revision 20080327

Typical values			REVISION 2000032
Properties	Unit (Si)	Values	Test methods
Polymer properties			
Melt flow rate (MFR)			ISO 1133
at 230 °C and 2.16 kg	g/10 min	14	
Density	kg/m³	905	ISO 1183
Mechanical properties			
Tensile test			ISO 527
stress at yield	MPa	22	
stress at break	MPa	19	
strain at break	%	600	
Flexural test			ASTM D 790
Flexural modulus	MPa	1200	
Izod impact notched			ISO 180/4A
at 23 °C	kJ/m²	No Break	
at 0 °C	kJ/m²	9.0	
at -20 °C	kJ/m²	6.0	
Charpy impact notched			ISO 179
at 23 °C	kJ/m²	31	
at 0 °C	kJ/m²	12.5	
at -20 °C	kJ/m²	7.0	
Hardness Shore D	-	66	ISO 868
Thermal properties			
Heat deflection temperature			
at 1.80 MPa (HDT/A)	°C	52	ISO 75/A
at 0.45 MPa (HDT/B)	°C	87	ISO 75/B
Vicat softening temperature			
at 10 N (VST/A)	°C	140	ISO 306/A
at 50 N (VST/B)	<u>°C</u>	<u>57</u>	ISO 306/B

All information supplied by or on behalf of any of the SABIC Europe companies in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but the relevant SABIC Europe company assumes no liability whatsoever in respect of application, processing or use of the afore-mentioned information or products, or any consequence thereof. The user undertakes all liability in respect of the application, processing or use of the afore-mentioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to any of the SABIC Europe companies for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the afore-mentioned information or products by the user.