

SABIC® HDPE P4200RT

HIGH DENSITY POLYETHYLENE FOR PIPE

DESCRIPTION

SABIC HDPE P4200RT is a high-density polyethylene (HDPE) with high melt viscosity for extrusion. The product provides excellent stress crack resistance properties (ESCR) combined with very good long-term hydrostatic strength, high heat & extremely high extraction stability. It fulfills the requirements of DIN 16833 / ISO 24033 for PE-RT Type II. The material is classified as MRS 10 (PE100) according to ISO 12162.

TYPICAL APPLICATIONS

Typical customer applications are underfloor heating and multilayer pipes for heating and plumbing. Further typical applications are High Voltage cable ducts, pipes for Oil & Gas exploration, district heating media pipes and casing pipes. It provides good ESCR (environmental stress cracking resistance). It is weldable, has very good heat aging resistance & good organoleptic properties. This grade is suitable for drinking water applications.

TYPICAL PROPERTY VALUES

Revision 20220720

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR) ⁽¹⁾			
@ 190°C & 5 kg load	0.45	g/10 min	ISO 1133
@ 190°C & 21.6 kg load	9.5	g/10 min	ISO 1133
Density			
@23°C	947	kg/m ³	ISO 1183
MECHANICAL PROPERTIES			
Hardness Shore D ⁽²⁾	59	-	ISO 868
Tensile Strength at Yield ⁽³⁾	22	MPa	ISO 527-2
Tensile Elongation at Yield ⁽³⁾	8	%	ISO 527-2
Tensile modulus ⁽³⁾			
Tensile modulus ⁽³⁾	850	MPa	ISO 899
Charpy Impact Notched @ 23°C ⁽²⁾	24	kJ/m ²	ISO 179
Charpy Impact Notched @ -30°C ⁽²⁾	8	kJ/m ²	ISO 179
MRS Classification ⁽⁴⁾			
FNCT, (4.0 MPa, 2% Arkopal N100, 800 C)	>350	Hrs	ISO 16770
THERMAL PROPERTIES			
Vicat Softening Point @ 10N (VST/A)	120	°C	ISO 306
Vicat Softening Point @ 50N (VST/B)	70	°C	ISO 306
Oxidation Induction Time (210°C)	>40	Minutes	ISO 11357-6

(1) Typical values & not to be construed as specification limits.

(2) Based on compression-molded sheet

(3) Test specimen according to ISO 527-2 type 1 BA, thickness 2mm with 50mm/min test speed.

(4) MRS classification testing ongoing.

PROCESSING CONDITIONS

Typical processing conditions for P4200RT: Melt temperature: 190-230°

FOOD REGULATION

P4200RT is suitable for Food contact application. Detailed information is provided in relevant Material Safety Datasheet and for additional specific information please contact SABIC local representative for certificate.

STORAGE AND HANDLING

Polyethylene material / compound should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions lead to quality deterioration and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.