



SABIC® PP QR6771K

POLYPROPYLENE RANDOM COPOLYMER FOR INJECTION MOLDING

DESCRIPTION

SABIC® QR6771K is a phthalate free high melt flow clarified polypropylene random copolymer grade for injection molding applications. This grade provides excellent clarity & surface gloss. It contains antistatic agent.

TYPICAL APPLICATIONS

SABIC® QR6771K can be used for producing transparent housewares, thin wall packaging items, appliances and caps & closures.

TYPICAL PROPERTY VALUES

Revision 20220721

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES ⁽¹⁾			
Melt Flow Rate (MFR)			
@ 230°C & 2.16kg load	70	g/10 min	ASTM D1238
Density			
@ 23°C	905	kg/m ³	ASTM D792
MECHANICAL PROPERTIES ⁽²⁾			
Tensile Properties			
Tensile Strength @ Yield	28	MPa	ASTM D638
Tensile Elongation @ Yield	12	%	ASTM D638
Flexural Modulus (1% Secant)	1100	MPa	ASTM D790 A
Notched Izod Impact Strength at 23°C	34	J/m	ASTM D256
Rockwell Hardness, R-Scale	94	-	ASTM D785
OPTICAL PROPERTIES			
Haze, 1 mm	10	%	ASTM D1003
THERMAL PROPERTIES			
Vicat Softening Point	130	°C	ASTM D1525
Heat Deflection Temperature at 455kPa	85	°C	ASTM D648

(1) Typical values; not to be construed as specification limits.

(2) Based on injection molded specimens

PROCESSING CONDITIONS

Typical processing conditions for SABIC® QR6771K are Barrel temperature range: 200 - 250°C. Mold shrinkage: 1.2 - 2.0% depending on wall thickness and processing conditions. Mold temperature: normally 15 - 40°C, up to 65°C for thick parts.

STORAGE AND HANDLING

Polypropylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PP resin within 6 months after delivery.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.