

Provisional Product Data Sheet

SUMITOMO PROPYLENE COPOLYMER **AZ764**

Block Copolymer, Injection

For industrial applications such as large crates, washing machine **Applications**

parts, electrical appliances, and thin walled articles.

High flow, high impact, high stiffness and high heat stability, with Characteristics

nucleating and antistatic agent.

Typical Processing Conditions 190 - 230°C Temperature

Mold Temperature 30°C

Typical Properties

Physical		Value	Unit	Method
Melt Flow Rate	2.16kg	<u>38</u>	g/10min	ASTM D1238
<u>Density</u>		<u>0.900</u>	g/cm³	<u>ASTM D792-A</u>
Mechanical		Value	Unit	Method
Tensile Strength	at Yield	<u>24</u>	<u>MPa</u>	<u>ASTM D638</u>
	at Break	16	MPa	ASTM D638
Tensile Elongation	<u>at Break</u>	<u>60</u>	<u>%</u>	ASTM D638
<u>Flexural Modulus</u>		<u>1200</u>	<u>MPa</u>	ASTM D790A
Izod Impact, Notched	<u>23°C</u>	<u>9</u>	kJ/m²	<u>ASTM D256</u>
	-20°C	6	kJ/m²	ASTM D256
Rockwell Hardness		<u>85</u>		<u>ASTM D785</u>
Thermal		Value	Unit	Method
Vicat Softening Temperature	<u>50N</u>	<u>67</u>	<u>°C</u>	ASTM D1525B
Heat Deflection Temperature	<u>0.45MPa</u>	<u>122</u>	<u>°C</u>	ASTM D648
Other		Value	Unit	Method
<u>Flammability</u>		<u>HB</u>		<u>UL 94</u>

The values shown are typical values measured on the product and are not to be considered as guaranteed specifications. Actual test results may vary. Test pieces preparation condition injection molding, nozzle temperature 220°C, mold temperature 50°C.



Manufacturer

AZ764 is manufactured in Saudi Arabia by Rabigh Refining & Petrochemical Co. (Petro Rabigh).

Food Contact Application

AZ764 has yet to be tested for the compliance to the US FDA Regulation 21 CFR 177.1520 for use in direct contact with food. Please contact your nearest SCA representative for more information.

Restriction of Hazardous Substances

The substances regulated under EU Directive 2002/95/EC on RoHS in electrical and electronic equipment are not used in the manufacturing process of AZ764 and are therefore not expected to be present.

Storage and Handling

AZ764 is supplied in 25kg bags or in bulk containers depending on packaging options available for different markets. It is advisable to store in a well ventilated storage facility, protected from rain, direct exposure to sunlight, temperature, and dust.

Moisture may accumulate inside the packaging if there is a significant fluctuation in ambient temperature and high relative humidity. If this occurs, customer is strongly advised to dry the resin prior to use. Direct exposure to sunlight and excessive ambient temperature may affect the properties, appearance, and odor characteristic of the resin.

Please refer to the Material Safety Data Sheet (MSDS) for information regarding industrial health and safety issues.

Disposal and the Environment

SCA prioritizes environmental management in all our operations in responsibility and respect towards the community and the world around us.

Unmodified, our polypropylene and polyethylene products are readily recyclable, both for reuse via reprocessing, and for energy reclamation through incineration. If disposed in landfills, our products, which are inert materials, do not pose pollution risks since they do not generate gaseous or liquid emissions.

Office Locations

SUMITOMO CHEMICAL ASIA PTE LTD

150 Beach Road #18-05/08 Gateway West SINGAPORE 189720

Phone +65 63035188 Fax +65 62989621 Web Site <u>www.sca.com.sg</u>

SUMITOMO CHEMICAL ASIA PTE LTD

Vietnam Representative Office, 7th Floor, Unit 701-3, Me Linh Point Tower, 2 Ngo Duc Ke Street, Dist. 01, Ho Chi Minh City VIETNAM Phone +84 8 35202767 Fax +84 8 35202911

SUMIKA PLASTICS AND CHEMICALS TRADING (SHANGHAI) CO., LTD.

Unit 46-07 Grand Gateway II, No.3 Hongqiao Road, Xu Hui District, Shanghai CHINA 200030

Phone +86 21 64482255 Fax +86 21 64077365

SUMIKA PLASTICS AND CHEMICALS TRADING (SHANGHAI) CO., LTD.

Unit 12E-2 Block C Peace Square, Shenghe Road, Nancheng District, Dongguan, Guangdong CHINA 523071

Phone +86 769 22887316 Fax +86 769 22887885

SCA SOUTH ASIA PETROCHEMICALS PRIVATE LIMITED

Sethi Chambers, Plot No.2, D.D.A. Local Shopping Centre, 2nd Floor, M.O.R. Land, New Rajinder Nagar, New Delhi, INDIA 110060 Phone +91 11 2874 1571 Fax: +91 11 2874 1565

SUMITOMO CHEMICAL EUROPE S.A./N.V.

Woluwelaan, 57, B-1830 Machelen BELGIUM

Phone +32 2 2548799 Fax +32 2 2512991 Web Site <u>www.sumitomo-chem.be</u>

SUMITOMO CHEMICAL EUROPE N.V.

Turkey Liaison Office, Fatih Sultan Mehmet Cad. Yayabeyi Sok. Ilayda Is Mrk, No.12/2, 34810 Kavacik, Beykoz - Istanbul - TURKEY Phone +90 216 680 3334 Fax: +90 216 680 1012

<u>Disclaimer</u>

The values shown are typical values measured on the product and are not to be considered as guaranteed specifications. All information contained in this document is provided in good faith and believed to be reliable on the date compiled. Customer is responsible to ensure that SCA materials, whether used alone or in conjunction with other materials, are suitable for the intended application. SCA accepts no liability whatsoever for any action taken based on this information, and/or for any loss and consequential loss or damage. Please contact your nearest SCA representative for more detailed information.

Page 2 of 2 Revision 20091002