

## Polypropylene 4170

### Technical Data Sheet Polypropylene – Impact Copolymer Produced in the United States



**TotalEnergies**

TotalEnergies Petrochemicals & Refining USA, Inc.  
Polymers Americas

#### Description

**Polypropylene 4170** is an impact copolymer with a low melt flow of 0.8 g/10min.

4170 polypropylene has a low fluidity providing melt strength with excellent impact properties

4170 is designed to be particularly suited for profile and sheet extrusion, extrusion-thermoforming, blown film, and corrugated cardboard manufacture.

#### Characteristics

	Method	Unit	Typical Value
<b>Rheological Properties</b>			
Melt Flow	D-1238	g/10 min	0.8
<b>Mechanical Properties<sup>(1)</sup></b>			
Tensile, Strength at Yield	D-638	psi (MPa)	3,900 (27)
Elongation at Yield	D-638	%	11
Flexural Modulus	D-790	psi (MPa)	165,000 (1,140)
Izod Impact Notched @ 23°C @ -20°C	D-256	ft.-lbs/in. (J/m)	No Break (No Break)
	D-256	ft.-lbs/in. (J/m)	1.5 (80)
<b>Thermal Properties<sup>(1)</sup></b>			
Melting Point	TOTAL Polypropylene Method	°F (°C)	320-329 (160-165)
Heat Deflection	D-648	°F (°C)	194 (90)
<b>Other Physical Properties</b>			
Density	D-1505	g/cm <sup>3</sup>	0.905

Polypropylene

(1) Data developed under laboratory conditions and are not to be used as specification, maxima or minima.

Rev: Sept 2021

TOTALENERGIES PETROCHEMICALS & REFINING USA, INC.  
POLYMERS AMERICAS  
1201 Louisiana Street  
Suite 1800  
Houston, TX 77002  
www.polymers.totalenergies.com

TECHNICAL CENTER  
P.O. Box 1200  
Deer Park, Texas 77536  
Phone: 281-884-7500

1-800-344-3462