

Pakro Kimya Dış Ticaret A.Ş.

İstoç Ticaret Merkezi Aktem Plaza Kat:5 Daire:33 Bağcılar/İstanbul 0212 659 26 01-02 www.pakrokimya.com.tr
0212 659 26 03 Info@pakrokimya.com.tr

Polypropylene 4252

TotalEnergies

Technical Data Sheet Polypropylene – Impact Copolymer Produced in the United States

TotalEnergies Petrochemicals & Refining USA, Inc. Polymers Americas

Description

Polypropylene 4252 is a 1.5 melt flow rate impact copolymer designed for improved toughness and high melt strength. This resin offers outstanding processability in combination with excellent mechanical properties. 4252 was specifically developed for the extruded corrugated sheet market.

High Purity: Low catalyst residues in Polypropylene 4252 allow extended processing runs without screen pack pluggage.

FDA: 4252 complies with all applicable FDA regulations for food contact applications.

Applications: 4252 is recommended for corrugated sheet, profile extrusion, blow molding, thermoforming, and slit film for carpet backing applications.

Processing: 4252 processes on conventional extrusion equipment with typical melt temperatures of 400°F-500°F (204°C-260°C).

Characteristics

	Method	Unit	Typical Value
Rheological Properties			
Melt Flow	D-1238	g/10 min	1.5
Mechanical Properties ⁽¹⁾			
Tensile, Strength at Yield	D-638	psi (MPa)	4,000 (28)
Elongation at Yield	D-638	%	6.5
Flexural Modulus	D-790	psi (MPa)	180,000 (1,240)
Izod Impact Notched @ 23°C	D-256A	ftIbs/in. (J/m)	No Break
Thermal Properties ⁽¹⁾			
Melting Point	TOTAL Method	°F (°C)	320-329 (160-165)
Heat Deflection	D-648	°F (°C)	203 (95)
Other Physical Properties			
Density	D-1505	g/cm ³	0.905

(1) Data developed under laboratory conditions and are not to be used as specification, maxima or minima.

Rev: Sept 2021

TOTALENERGIES PETROCHEMICALS & REFINING USA, INC. POLYMERS AMERICAS 1201 Louisiana Street Suite 1800 Houston, TX 77002 www.polymers.totalenergies.com

TECHNICAL CENTER P.O. Box 1200 Deer Park, Texas 77536 Phone: 281-884-7500

1-800-344-3462

All tests were run under laboratory conditions. ASTM (where applicable) testing procedures. The data are intended as a general guide only and do not necessarily represent results that may be obtained elsewhere. The use of TotalEnergies products must be guided by the users own methods for selection of proper formulation. TotalEnergies Betrochemicals & Refining USA Inc. disclaims any responsibility for misuse or misapplication of its products. TotalEnergies MACES NO WARRANTY THAT GOODS SUPPLIED SHALL BE FIT FOR ANY PARTICULAR PURPOSE. TotalEnergies Inditional and the second of the service remedy for any claims arising out of sales of its products are expressly limited at customer option to replacement of non-performing goods or payment not to exceed the purchase price plus transportation charges thereon in respect to any material which damage is claimed.