







Polystyrene 535B

Technical Data Sheet Polystyrene - Crystal Produced in the United States

TotalEnergies Petrochemicals & Refining USA, Inc. **Polymers Americas**

Description

Polystyrene 535B: Is a high heat crystal polystyrene designed for injection molding, extrusion, and blow molding. The material demonstrates excellent strength and good temperature resistance.

Application:

Electronics packaging

Cutlery

Office accessories

Medical

Appliance components

General Information:

This material complies with FDA requirements as described in 21 CFR §177.1640.

This material holds Underwriters Laboratory recognition 94HB; see UL File E55470 at www.UL.com.

USP Class VI

Material Safety Data Sheets are available to help customers satisfy their safety needs.

Characteristics

	Method	Unit	Typical Value
Rheological Properties			
Melt Flow (200°C-5kg)	D-1238	g/10mn	4.0
Mechanical Properties			
Tensile Strength	D-638	psi	7,400
Tensile Modulus	D-638	psi (10 ⁵)	4.3
Flexural Strength	D-790	psi	14,000
Flexural Modulus	D-790	psi (10 ⁵)	4.5
Thermal Properties			
Heat Distortion - Annealed	D-648	°F	208
Vicat Softening	D-1525	°F	222
Other Physical Properties			
Density		g/cm ³	1.04
Linear Shrinkage	D-955	in/in	.004007
Moisture		%	<0.1

Rev: Sept 2021

TOTALENERGIES PETROCHEMICALS & REFINING USA, INC. POLYMERS AMERICAS 1201 Louisiana Street Suite 1800 Houston, TX 77002 www.polymers.totalenergies.com

TECHNICAL CENTER P.O. Box 1200 Deer Park, Texas 77536 Phone: 281-884-7500

1-800-344-3462