Technical Data Sheet Polypropylene - Random Copolymer **Produced in the United States**

TotalEnergies Petrochemicals & Refining USA, Inc. **Polymers Americas**

Description

Polypropylene 7450HC Low catalyst results in improved color stability.

Clarity/Impact: 7450HC improves its clarity and impact resistance over conventional homopolymer films.

Heat Sealable: 7450HC makes it suitable as a heat seal layer for oriented films.

Slip/Antiblock: 7450HC is formulated with a high level of antiblock additive for improved film handling.

FDA: 7450HC complies with all applicable FDA regulations for food contact applications.

Applications: 7450HC is recommended for use in either non-oriented cast film processes for manufacture of packaging films that require improved optical and impact properties, or as a heat seal layer for oriented films.

Processing: 7450HC resin processes on film extrusion equipment with typical melt temperatures of 450°F-525°F (232°C-274°C).

Characteristics

	Method	Unit	Typical Value	
Rheological Properties				
Melt Flow	D-1238	g/10 min	5.0	
Film Properties, Non-Oriented ⁽¹⁾				
Ultimate Tensile	D-882	psi (MPa)	4,000 (28)	
1% Secant Modulus	D-882	psi (MPa)	80,000 (550)	
Elongation at Break	D-882	%	400	
MVTR @ 100°F, 90% RH	E-96	g/100 sq-in/24 hrs/mil	0.7	
Dart Impact (F50)	D-1709	g/mil	45	
Haze	D-1003	%	3	
Gloss, 45°	D-2457	%	80	
Heat Seal Temperature	F-88 ⁽³⁾	°F (°C)	270 (132)	
Thermal Properties ⁽¹⁾⁽²⁾				
Melting Point	DSC	°F (°C)	289 (143)	
Other Physical Properties				
Density	D-1505	g/cc	0.90	

⁽¹⁾ Data developed under laboratory conditions and are not to be used as specification, maxima or minima.

Rev: Sept 2021

TOTALENERGIES PETROCHEMICALS & REFINING USA, INC. POLYMERS AMERICAS 1201 Louisiana Street Suite 1800 Houston, TX 77002 www.polymers.totalenergies.com

TECHNICAL CENTER P.O. Box 1200 Deer Park, Texas 77536 Phone: 281-884-7500

1-800-344-3462

 ⁽²⁾ MP determined with a DSC-2 Differential Scanning Calorimeter. Test procedure available upon request.
(3) Minimum seal strength is 200 g/inch at 15 psi pressure and 1 sec.