



TotalEnergies

Refining & Chemicals
Polymers

Polypropylene Lumicene® MR 2002

Technical data sheet
Polypropylene – Metallocene Homopolymer
Produced in Europe

Description

Polypropylene Lumicene® MR 2002 is a metallocene polypropylene with a Melt Flow Index of 15 g/10 min.

Polypropylene Lumicene® MR 2002 is characterized by high fluidity for high speed spinning on spun laid non-woven lines where spun filaments are produced to form a web that is then thermally bonded to manufacture products for hygienic and technical uses.

Polypropylene Lumicene® MR 2002 has a special anti gas-fading formulation to reduce yellowing in fibres.

Characteristics

	Method	Unit	Typical Value
Rheological properties			
Melt Flow Index 230°C/2.16 kg	ISO 1133	g/10 min	15
Mechanical properties			
Flexural modulus	ISO 178	MPa	1300
Thermal properties			
Melting Point	ISO 3146	°C	151
Other physical properties			
Density	ISO 1183	g/cm ³	0.905
Bulk Density	ISO 1183	g/cm ³	0.525

Handling and storage

Please refer to the safety data sheet (SDS) for handling and storage information. It is advisable to convert the product within one year after delivery provided storage conditions are used as given in the SDS of our product. SDS may be obtained from the website: www.polymers.totalenergies.com.

Information contained in this publication is true and accurate at the time of publication and to the best of our knowledge. The nominal values stated herein are obtained using laboratory test specimens. These are typical values not to be construed as specification limits. Before using one of the products mentioned herein, customers and other users should take all care in determining the suitability of such product for the intended use. Unless specifically indicated, the products mentioned herein are not suitable for applications in the pharmaceutical or medical sector. The Companies within TotalEnergies Petrochemicals do not accept any liability whatsoever arising from the use of this information or the use, application or processing of any product described herein. No information contained in this publication can be considered as a suggestion to infringe patents. The Companies disclaim any liability that may be claimed for infringement or alleged infringement of patents.