

Pakro Kimya Dış Ticaret A.Ş.

İstoç Ticaret Merkezi Aktem Plaza Kat:5 Daire:33 Bağcılar/İstanbul 0212 659 26 01-02 www.pakrokimya.com.tr
0212 659 26 03 Info@pakrokimya.com.tr

## DaelimPoly UH563S

Homopolymer



## Product Description

DaelimPoly UH563S is the controlled rheology polypropylene homopolymer manufactured by UlsanPP under the license of Lyondellbasell using Spheripol process. This product is typically used in spunbonded nonwovens. DaelimPoly UH563S resin meets the FDA requirements in the Code of Federal Regulations in 21 CFR 177.1520 for food contact.

Features Excellent spinnability / Excellent drawability / Anti-gas fading
Market Textile
Application Diaper and sanitary napkin / Agriculture / Shopping bag / Apparel cover / Wettissues

ASTM Data			
Typical Properties	Nominal Value	Units	Test Method
Melt Flow Rate (230°C,2.16kg)	38	g/10 min	ASTM D1238L
Density	0.9	g/cm3	ASTM D1505
Flexural Modulus	15000	kg/cm2	ASTM D790
Tensile Strength at Yield	380	kg/cm2	ASTM D638
Elongation at Yield	8	%	ASTM D638
Izod Impact Strength (23°C)	3	kgfcm/cm	ASTM D256
Rockwell Hardness	98	R-Scale	ASTM D785
Vicat Softening Point	153	°C	ASTM D1525
HDT (0.46 N/mm²)	100	°C	ASTM D648

1) The above values are typical property values for reference only not be construed as specification limits.

2) Beforeusing UlsanPP product, users shall review carefullySeller's instructions for the use of such productand make their ownindependent determination of whether the product is suitable for the intended use and can be used safely and legally. If users fail to comply with Seller's restrictions and instructions for the use of the product or an obligation to notify Seller, if applicable, of each specific application before using such product in certain categories of application, users are solely liable for any injuries or damages resulting from their use of such product and Seller shall have no liabilitywhatsoever.

3) ULSANPP MAKES NO WARRANTY, EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE) UNLESS AGREED OTHERWISE IN A CONTRACT.

4) The use of this product(s) is strictly prohibited in

- i. U.S. FDA Class III, Health Canada Class IV, and/or European Union Class III MedicalDevices;
- ii. applications involving permanent implantation into the body;
- iii. life-sustaining medical applications; or
- iv. lead, asbestos or MTBE related applications.

Users are solely liable for any injuries or damages resulting from any use of this product(s) in the above categories and Seller shall have no liability whatsoever. 5) The use of this product is further prohibited in the following categories unless Seller receives a prior notice of each specific application using such product, provided that Seller may refuse to sell such product at its sole discretion.

- i. U.S. FDA Class I, Health Canada Class I, and/or European Union Class I medicaldevices;
- ii. U.S. FDA Class II, Health Canada Class II or Class III, and/or European Union Class II Medical Devices;
- iii. film, overwrap and/or product packaging that is considered a part or component of one of the aforementioned Medical Devices;
- iv. packaging in direct contact with an active pharmaceutical ingredient and/or dosage form that is intended for inhalation, injection, intravenous, nasal, ophthalmic (eye), digestive, or topical (skin) administration;
- v. tobacco related products and applications;
- vi. electronic cigarettes and similar devices; or
- vii. pressure pipe or fittings that are considered a part or component of a nuclear reactor

※ All references to U.S. FDA, Health Canada, and European Union regulations include another country's equivalent regulatory classification.
6) For the purpose of this Disclaimer, "Seller" shall mean UlsanPP and any person or entity appointed by UlsanPP for the sale of the product covered by this Disclaimer. Users should review the applicable Material Safety Data Sheet before handling the product.

## **Trademarks**

The Trademark referenced within the product name is owned and used by the DL Chemical Co., Ltd. and it is used by Ulsan PP Co., Ltd.